

# TYPE APPROVAL CERTIFICATE

**BV W/b S bWg(**

**BV bVS 5Z aa 4W S Rc ba**

with type designation(s)

**E dS dW a) 3E 3E 3E 3E 3E R 3E**

Issued to

**8caVW5 c 1 : bR**

**B f W H6387 5, 1VW**

is found to comply with

**2 D 5: cSa T Z aaVW bW 6 WV a SSR R ZVWb Tb**  
**2Sb a SDS W a Bg S d Z S' BTc 2 Sb a S ' ' '**



**Rc bRSa WbW**

Woven Roving; **3E** , **3E** , **3E** , **3E** , **3E** and **3E** .

E: E-Glass  
WR: Woven Roving  
270, 360, 500, 580, 800: Weight per unit area, g/m<sup>2</sup>

The following indicative properties have been verified by Type Testing of laminates:

<b>S bWa</b>	<b>BSab ; SbV R</b>	<b>3E</b>	<b>3E</b>	<b>3E</b>		
Tensile Strength – warp	ISO 527-1,4	395.52	436.75	393.43	mean	MPa
Tensile Modulus – warp	ISO 527-1,4	24.62	25.89	22.16	msv	GPa
Tensile Elongation – warp	ISO 527-1,4	2.23	2.39	2.47	mean	%
Tensile Strength – weft	ISO 527-1,4	424.17	372.48	438.29	mean	MPa
Tensile Modulus – weft	ISO 527-1,4	26.22	23.48	23.71	msv	GPa
Tensile Elongation – weft	ISO 527-1,4	2.16	2.38	2.59	mean	%
Fibre content	ISO 1172	65.02 (0) 63.84 (90)	61.40 (0) 61.85 (90)	62.06 (0) 61.86 (90)	mean	%
Resin	TM-107					
Curing Procedure used for Type Testing	24 hrs at room temperature, 4 hrs at 80°C					

<b>S bWa</b>	<b>BSab ; SbV R</b>	<b>3E</b>	<b>3E</b>	<b>3E</b>		
Tensile Strength – warp	ISO 527-1,4	457.78	477.94	428.33	mean	MPa
Tensile Modulus – warp	ISO 527-1,4	24.77	26.30	22.84	msv	GPa
Tensile Elongation – warp	ISO 527-1,4	2.54	2.58	2.69	mean	%
Tensile Strength – weft	ISO 527-1,4	351.47	416.87	310.81	mean	MPa
Tensile Modulus – weft	ISO 527-1,4	22.83	24.40	20.13	msv	GPa
Tensile Elongation – weft	ISO 527-1,4	2.40	2.47	2.75	mean	%
Fibre content	ISO 1172	61.18 (0) 60.66 (90)	65.52 (0) 64.85 (90)	62.67 (0) 61.28 (90)	mean	%
Resin	TM-107					
Curing Procedure used for Type Testing	24 hrs at room temperature, 4 hrs at 80°C					

(0): fibre content for warp laminates  
(90): fibre content for weft laminates

:  
= Manufacturer's Specified Value (verified to be within mean - 10% of Type Test results)  
= Mean of Type Test results

**ZW bW : W W bW**

Any significant changes in design and / or quality of the material will render the approval invalid.

**Bg S d ZR c S b bW**

1. Previous of Type Approval Certificate No. K-6308.

Job Id:  
Certificate No: **B 9 B6**

2. Assessment Report from DNV GL Shanghai of 2019-05-10.
3. Testing Center, Jushi Group Co., Ltd. Report Nos. BG190325101 (EWR270), BG190325102 (EWR360), BG190325103 (EWR500), BG190325104 (EWR580), BG190325105 (EWR600), BG190325106 (EWR800) of 2019-03-25.
4. ISO 9001 Audit Report (DEKRA).
5. Application for Type Approval of 2019-03-25.
6. Email from DNV GL Shanghai of 2015-05-05, incl. Assessment Report of 2015-05-05 and Application Letter from Jushi of 2015-01-29.
7. Email from DNV Shanghai of 2011-05-09, incl. Survey Report of 2011-05-09, Declaration of Conformity from Jushi of 2011-04-08, Application Letter from Jushi of 2011-04-08 and DNV Approval Documents 2011 issued by Jushi, Test Report Nos. BG110402004 and BG110402005 of 2011-04-02.

**BSaba WR cb**

Type Testing carried out in accordance with **Bg S d ZR c S b bW** .

Note that the DNV GL Class Programme DNVGL-CP-0467 – Type approval – Uni- and multi-axial multi-ply fabrics made of glass fibres, is not dedicated for these kind of products, hence the DNV TAP No. 1-501.8 may be used as reference for these kind of products until a specific DNVGL-CP may be established.

**; W T Rc b**

Product shall be marked with **; 8caVW5 c 1 :bR 1VW** and .

The marking is to be carried out in such a way that it is visible, legible and indelible. The marking of product is to enable traceability to the DNV GL Type Approval Certificate.

**S WRW Z aaSaa S b**

The scope of the Periodical Assessment is to verify that the conditions stipulated for the Type Approval is complied with and that no alterations are made to the product design or choice of materials.

Periodical assessments (for Certificate Retention and Certificate Renewal) shall be performed according to DNVGL-CP-0338.

This certificate is only valid if required Periodical assessments are carried out with satisfactory results. To check the validity of this certificate, please look it up in <https://approvalfinder.dnvgl.com>

END OF CERTIFICATE